

Attorney Docket No. 09792909-4817

PATENT

## IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Patent Application of:

H. Tsujimoto et al.

Application No. 09/822,926


Filed: March 30, 2001

For: MATERIAL FOR POSITIVE  
ELECTRODE AND SECONDARY  
BATTERY

Group Art Unit: 1746

Examiner: Jonathan Crepeau

I hereby certify that this document is being sent via  
facsimile to the attention of Examiner Jonathan Crepeau  
at the United States Patent and Trademark Office, on  
December 3, 2004.

  
Roxanne M. Swartz

Commissioner for Patents  
P.O. Box 1450  
Alexandria, VA 22313-1450

**IN THE CLAIMS**

1. (Currently Amended) A non-aqueous electrolyte secondary battery comprising a positive electrode, a negative electrode and a non-aqueous electrolyte, wherein the positive electrode contains:
- (a) a manganese-contained complex oxide containing:
- (i) lithium (Li);
- (ii) manganese (Mn);
- (iii) a first element (Ma) selected from the group consisting of zinc (Zn), cobalt (Co), aluminum (Al), tin (Sn), chromium (Cr), and magnesium (Mg), wherein the chemical formula of the manganese-contained complex oxide is  $\text{Li}_x\text{Mn}_{2-y}\text{Ma}_y\text{O}_4$  and wherein x is the range of  $0.9 \leq x \leq 2.0$  and y is in the range of  $0.01 \leq y \leq 0.50$ , both inclusive; and
- (b) a nickel-contained complex oxide containing:
- (i) lithium (Li);

Application No. 09/822,926

Page 2

(ii) nickel (Ni);

(iii) a second element selected from the group consisting of iron (Fe), zinc (Zn), cobalt (Co), aluminum (Al), tin (Sn), chromium (Cr), and magnesium (Mg), wherein the chemical formula of the nickel-contained complex oxide is  $\text{LiNi}_{1-z}\text{Ma}_z\text{O}_2$  and wherein z is the range of  $0.01 \leq z \leq 0.05$  0.50, both inclusive; and

~~(c) wherein cobalt (Co) is contained in not more than one of the manganese combined complex oxide and the nickel contained complex oxide.~~

2. (Original) The non-aqueous electrolyte secondary battery of claim 1, wherein a mixing ratio of the nickel-contained complex oxide to the manganese-contained complex oxide in the positive electrode, in terms of mass ratio (nickel-contained complex oxide/manganese-contained complex oxide), lies within the range of 90/10 to 10/90.

Claims 3-6 (Cancelled)

7. (Original) The non-aqueous electrolyte secondary battery of claim 1, wherein at least either the positive electrode or the negative electrode includes a positive electrode mixture layer or a negative electrode mixture layer provided on both sides or one side of a positive electrode collector layer or a negative electrode collector layer.

8. (Original) The non-aqueous electrolyte secondary battery of claim 1, wherein the negative electrode contains a material capable of occluding and releasing lithium.

Application No. 09/822,926

Page 3

9. (Original) The non-aqueous electrolyte secondary battery of claim 1, wherein the negative electrode contains at least one material selected from the group consisting of a metal and a semiconductor capable of forming an alloy and a compound with lithium, an alloy and a compound of the metal and the semiconductor, a carbon material, a metal oxide, and a polymer material.

10. (Original) The non-aqueous electrolyte secondary battery of claim 9, wherein the negative electrode contains at least one material selected from the group consisting of non-graphitizing carbon, artificial graphite, coke, graphite, glasslike carbon, polymer organic compound calcined materials, carbon fiber, activated carbon and carbon black.

11. (Original) The non-aqueous electrolyte secondary battery of claim 9, wherein the negative electrode contains at least one material selected from the group consisting of a Group 4B metal element, a semiconductor element, and an alloy and a compound of the metal element and the semiconductor element.

12. (Original) The non-aqueous electrolyte secondary battery of claim 9, wherein the negative electrode contains at least one material selected from the group consisting of silicon (Si), tin (Sn), and an alloy and a compound of silicon and tin.

13. (Original) The non-aqueous electrolyte secondary battery of claim 1, wherein: the positive electrode and the negative electrode includes a positive electrode mixture

Application No. 09/822,926

Page 4

layer or a negative electrode mixture layer provided on both sides of either a positive electrode collector or a negative electrode collector made of a band-shaped metal foil; and

wherein the positive electrode and the negative electrode are stacked with a microporous separator interposed therebetween and are rolled spirally.

14. (Original) The non-aqueous electrolyte secondary battery of claim 1, wherein the electrolyte contains lithium salt and solvent; wherein:

the solvent contains at least one material selected from the group consisting of propylene carbonate, ethylene carbonate, diethyl carbonate, dimethyl carbonate, 1,2-dimethoxyethane, 1,2-diethoxyethane,  $\gamma$ -butyrolactone, tetrahydrofuran, 2-methyl tetrahydrofuran, 1,3-dioxolane, 4-methyl-1,3-dioxolane, diethyl ether, sulfolane, methyl sulfolane, acetonitrile, propionitrile, anisole, ester acetate, ester butyrate and ester propionate.

15. (Original) The non-aqueous electrolyte secondary battery of claim 1, wherein the electrolyte contains at least one electrolyte selected from the group consisting of a gel electrolyte in which an electrolyte solution containing lithium salt is held in a polymer compound, a solid electrolyte in which lithium salt is dispersed onto a polymer compound having an ion conductivity, and an electrolyte made of solid inorganic conductor.

16. (Currently Amended) A material for a positive electrode containing:

(a) a manganese-contained complex oxide containing:

(i) lithium (Li);

(ii) manganese (Mn);

Application No. 09/822,926  
Page 5

(iii) a first element selected (Ma) from the group consisting of zinc (Zn), cobalt (Co), aluminum (Al), tin (Sn), chromium (Cr), and magnesium (Mg), wherein the chemical formula of the manganese-contained complex oxide is  $\text{Li}_x\text{Mn}_{2-y}\text{Ma}_y\text{O}_4$  and wherein x is the range of  $0.9 \leq x \leq 2.0$  and y is in the range of  $0.01 \leq y \leq 0.50$ , both inclusive; and

(b) a nickel-contained complex oxide containing:

(i) lithium (Li);

(ii) nickel (Ni);

(iii) a second element selected from the group consisting of iron (Fe), zinc (Zn), cobalt (Co), aluminum (Al), tin (Sn), chromium (Cr), and magnesium (Mg), wherein the chemical formula of the nickel-contained complex oxide is  $\text{LiNi}_{1-z}\text{Ma}_z\text{O}_2$  and wherein z is the range of  $0.01 \leq z \leq 0.50$ , both inclusive;

~~(c) wherein cobalt (Co) is contained in not more than one of the manganese combined complex oxide and the nickel-contained complex oxide; and~~

(dc) wherein a mean particle size of the manganese-contained complex oxide and the nickel-contained complex oxide is 30 microns or less.

Claims 17-19 (Canceled).

20. (Previously Presented) The non-aqueous electrolyte secondary battery of claim 16, wherein a mixing ratio of the nickel-contained complex oxide to the manganese-contained complex oxide in the positive electrode, in terms of mass ratio (nickel-contained complex oxide/manganese-contained complex oxide), lies within the range of 90/10 to 10/90.

Application No. 09/822,926

Page 6

21. (Previously Presented) The non-aqueous electrolyte secondary battery of claim 16, wherein at least either the positive electrode or the negative electrode includes a positive electrode mixture layer or a negative electrode mixture layer provided on both sides or one side of a positive electrode collector layer or a negative electrode collector layer.

22. (Previously Presented) The non-aqueous electrolyte secondary battery of claim 16, wherein the negative electrode contains a material capable of occluding and releasing lithium.

23. (Previously Presented) The non-aqueous electrolyte secondary battery of claim 16, wherein the negative electrode contains at least one material selected from the group consisting of a metal and a semiconductor capable of forming an alloy and a compound with lithium, an alloy and a compound of the metal and the semiconductor, a carbon material, a metal oxide, and a polymer material.

24. (Previously Presented) The non-aqueous electrolyte secondary battery of claim 23, wherein the negative electrode contains at least one material selected from the group consisting of non-graphitizing carbon, artificial graphite, coke, graphite, glasslike carbon, polymer organic compound calcined materials, carbon fiber, activated carbon and carbon black.

25. (Previously Presented) The non-aqueous electrolyte secondary battery of claim 23, wherein the negative electrode contains at least one material selected from the group

Application No. 09/822,926  
Page 7

consisting of a Group 4B metal element, a semiconductor element, and an alloy and a compound of the metal element and the semiconductor element.

26. (Previously Presented) The non-aqueous electrolyte secondary battery of claim 23, wherein the negative electrode contains at least one material selected from the group consisting of silicon (Si), tin (Sn), and an alloy and a compound of silicon and tin.

27. (Previously Presented) The non-aqueous electrolyte secondary battery of claim 2, wherein: the positive electrode and the negative electrode includes a positive electrode mixture layer or a negative electrode mixture layer provided on both sides of either a positive electrode collector or a negative electrode collector made of a band-shaped metal foil; and wherein the positive electrode and the negative electrode are stacked with a microporous separator interposed therebetween and are rolled spirally.

28. (Previously Presented) The non-aqueous electrolyte secondary battery of claim 2, wherein the electrolyte contains lithium salt and solvent; wherein: the solvent contains at least one material selected from the group consisting of propylene carbonate, ethylene carbonate, diethyl carbonate, dimethyl carbonate, 1,2-dimethoxyethane, 1,2-diethoxyethane,  $\gamma$ -butyrolactone, tetrahydrofuran, 2-methyl tetrahydrofuran, 1,3-dioxolane, 4-methyl-1,3-dioxolane, diethyl ether, sulfolane, methyl sulfolane, acetonitrile, propionitrile, anisole, ester acetate, ester butyrate and ester propionate.

Application No. 09/822,926  
Page 8

29. (Previously Presented) The non-aqueous electrolyte secondary battery of claim 2, wherein the electrolyte contains at least one electrolyte selected from the group consisting of a gel electrolyte in which an electrolyte solution containing lithium salt is held in a polymer compound, a solid electrolyte in which lithium salt is dispersed onto a polymer compound having an ion conductivity, and an electrolyte made of solid inorganic conductor.